# **CEMLINE BB-W**



# INSTRUCTIONS FOR USE (IFU) 15.12.2015/1<sup>st</sup> issue

#### PRODUCT DESCRIPTION

CEMLINE BB-W is a cementitious, surface waterproofer. For application CEMLINE BB-W powder is mixed with water.

#### **Packaging**

25 kg PE-lined paper bag

#### <u>Storage</u>

When stored in a dry place in unopened, undamaged original packaging, shelf life is 12 months.

#### **AREAS OF APPLICATION**

- substrates: concrete and masonry
- against active and passive water pressure
- protection against water and humidity
- walls, etc.
- drinking water structures

#### **SURFACE PREPARATION**

The substrate to be treated must be sound and even, open-pored, roughened and its surface free from voids, large cracks or ridges. Any adhesion reducing substances like bitumen, oil, grease, remains of paint or laitance must be removed by suitable means. Water leaks must be stopped e.g. with VANDEX PLUG.

Thoroughly moisten the substrate, it must be damp but not wet at the time of application. Any surface water on horizontal surfaces must be removed.

#### **MIXING**

Mix 25 kg of CEMLINE BB-W with 5-6.25 litres of tap water in a clean container for at least 3 minutes to a lump-free, homogeneous consistency. Use a mechanical mixer.

#### **APPLICATION**

CEMLINE BB-W is applied with brush, trowel or suitable spray equipment.

A maximum of 2 mm (approx. 4 kg/m²) can be applied in one working cycle. In most cases the application of more than one coat is recommended; please refer to

relevant specification. It is recommended to apply the next coat whilst the previous coat is still damp on the surface. The previous coat must not be damaged during application of the following coat. The waiting time before applying the following coat depends on local climatic conditions such as humidity, temperature, etc. The previous coat is textured by suitable means whilst still plastic to form a key. To maintain workability of the material do not add water, simply re-stir the mixture. Workability at 20 °C approx. 45 minutes.

#### Brush application

Ensure that all cavities in the substrate are filled.

#### <u>Trowel application</u>

First a scratch coat is applied for maximum adhesion to the substrate, working from the bottom up. Ensure that all cavities in the substrate are filled in order to exclude any trapped air.

#### Spray application

CEMLINE BB-W can be applied with a suitable fine mortar spraying device.

For maximum spray pattern it should be possible to adjust volume of product as well as air pressure and volume. The nozzle diameter is approx. 6 mm.

The first layer of Vandex is applied in a circular motion with the spray nozzle held at a 90° angle to the substrate. The material is then flattened and keyed. The final layer can be left as a spray finish or treated to a specified finish.

Do not apply at ambient temperatures below +5 °C, or to a frozen substrate.

#### **CONSUMPTION**

Type of water impact	Recommended overall appli- cation rate	Total layer thickness (approx.)
Pressureless water	4 kg/m²	2 mm
Water under pressure	6 kg/m²	3 mm

Substrate and application conditions have to be observed. Depending on surface roughness, consumption may

## **CEMLINE BB-W**



#### **CURING**

Provide a relative humidity of > 85% in enclosed areas and avoid formation of water films or condensation on top of coating during 7 days after application.

Keep surfaces exposed to weathering damp for at least 5 days and provide suitable protection against extreme weather conditions (e.g. sun, wind, frost) while setting. The freshly treated surfaces should be protected from rain for a minimum period of 24 h.

### FILLING OF WATER RETAINING STRUCTURES

Filling can take place when the surface treatment has hardened sufficiently, usually not less than

21 days after application at a curing temperature ≥ 7 °C

14 days after application at a curing temperature ≥ 15 °C

7 days after application at a curing temperature ≥ 20 °C

and provided that the surface is thoroughly checked for hardness.

The required cure time may be calculated from the minimum daily temperature recorded by the water company's representative, or if no records are kept, 21 days minimum.

#### **CLEANING AND DISINFECTION**

A careful cleaning and disinfection prior to the first operation is essential. Observe national laws and regulations (e.g. Principles of Water Supply Hygiene & Technical Guidance Note No. 8 "Water treatment [disinfection]").

Cleaning and disinfection of the tanks prior to the first filling

A careful cleaning and disinfection prior to the first operation is essential:

- rinsing of all inner surfaces (ceiling, walls, floor, columns, stairs) with drinking water (pressure ≤ 30 bar)
- disposing of the rinsing water

The use of detergents prior to the first operation is generally not necessary.

For disinfection all inner surfaces have to be treated with approved disinfectants (e.g. aqueous solutions of sodium hypochlorite, calcium hypochlorite etc.) and afterwards rinsed with clear water.

The disinfectant contaminated water has to be disposed of according to legal requirements (also refer to Principles of Water Supply Hygiene & Technical Guidance Note No. 14 "Disposal of chlorinated water").

At the time of filling the tank samples for bacteriological analysis shall be taken. When the samples are approved to comply with legal requirements the tank can be put into operation.

#### Periodical cleaning and disinfection

The drinking water tanks shall be cleaned periodically (min. once a year) and disinfected if necessary.

For the cleaning water jetting and the use of appropriate mechanical equipment is suitable. Chemical detergents shall only be used exceptionally, increasing the water pressure and careful scrubbing brings in most cases the same effect.

The water tank shall be cleaned immediately after emptying as the residues can be removed more easily when still humid.

Suitable means for the cleaning:

- combined brushing (scrubbing) and rinsing with water (≤ 30 bar)
- water jetting (≤ 30 bar)

The use of chemical detergents shall be reduced to a minimum and prior to application be discussed with the local Vandex distributor.

Chemical additives to the cleaning water reduce the cleaning time and shall be applied only to remove very resistant residues. Acid containing detergents attack cement based Vandex coatings. In order to prevent damages Vandex coatings shall be exposed to aggressive detergents only for a short period.

Furthermore, the following recommendations shall be considered:

- Chemical detergents must be assessed for their toxicology and drinking water suitability prior to their application. They must comply with the corresponding food laws. It is highly recommended to apply only detergents which are approved for contact with drinking water. This includes also assessments regarding potential consequences on the microbiology of the water, the compatibility with the coating material, the disposal and work and safety related issues.
- It has to be checked if and under which conditions the detergent containing water can be disposed of safely into the municipal wastewater system.

# **CEMLINE BB-W**



 Adverse effects of the cleaning on the inner surfaces or mounting parts, e.g. roughening or corrosion, shall be kept as little as possible.

#### **ADDITIONAL INFORMATION**

The grey CEMLINE BB-W treatment is not a decorative finish. Discolouration of the treated surface may occur.

#### **HEALTH AND SAFETY**

For safe handling procedures and precautions, instructions on safe disposal of spillage and excess product, avoidance of harm to the environment etc. please refer to Safety Data Sheet of CEMLINE BB-W.

The information contained herein is based on our long-term experience and the best of our knowledge. We can, however, make no guarantee since for a successful outcome, all circumstances in an individual case must be taken into consideration. Indications of quantities required are only averages which in certain cases might be greater.



An RPM company

HEAD OFFICE AND INTERNATIONAL SALES:

Vandex International Ltd

P.O. Box · CH-4501 Solothurn/Switzerland +41 32 626 36 36 · info@vandex.com · www.vandex.com



Vandex Isoliermittel-Gesellschaft m.b.H.

P.O. Box · D-21487 Schwarzenbek/Germany





