CEMLINE TAPE



High performance sealing tape for movements and construction joints

- permanent flexible waterproofing seal
- high elasticity depending on the thickness of the tape and width of the expansion zone
- thermal welding ensures secure, watertight joints

PRODUCT DESCRIPTION

CEMLINE TAPE is a thermoplastic elastomer (TPE). Extremely durable, it has excellent resistance to weathering and is UV and chemically stable.

The bond to the substrate is achieved using an adhesive.

AREAS OF APPLICATION


The CEMLINE TAPE system bridges and seals expansion and construction joints, as well as cracks in concrete structures.

The maximum permissible expansion under continuous load depends on the thickness of the tape and the width of the non bonded expansion zone.

The CEMLINE TAPE system is resistant to hydrostatic pressure on the active side. On the passive side, in combination with a counterpressure structure.

APPLICATION

- The substrate must be sound, clean and free of dust, oil and grease. Sandblasting, high pressure waterjetting or grinding are recommended for the initial preparation. Any unevenness or other surface irregularities must be levelled off prior to application. The acceptable moisture content of the substrate depends on the type of adhesive
- 2. Apply the adhesive as an initial coating to both sides of the joint or crack with a trowel or toothed comb. With expansion joints, an expansion zone of sufficient width is to be left free of adhesive.
- Press the CEMLINE TAPE firmly into the adhesive before
 it hardens. Any entrapped air must be worked out.
 Where greater than normal movement is anticipated, it
 is advisable to leave some slack in the tape in the expansion zone.
- 4. Float the final coating by trowel. In the case of expansion joints, an expansion zone must be kept free of adhesive. In case of any necessary overcoating, the adhesive must be sprinkled with quartz sand.
- Protect the CEMLINE TAPE against possible mechanical damage throughout application by appropriate means, such as sheet metal, rubber matting or polystyrene slabs. The CEMLINE TAPE must be protected against heat loads exceeding of 70 °C.



CEMLINE TAPE - Sealing of an expansion joint.

PACKAGING

Туре	Thickness	Width	Length	Recommended use
200/2 200/1		200 mm 200 mm	20 m 20 m	movement joints cracks, construction joints
150/1		150 mm	20 m	cracks, construction joints

Other types on request.

STORAGE

In unopened and undamaged original packaging, the tape can be stored in a dry atmosphere for an unlimited period of time (optimal storage conditions: $(20 \, ^{\circ}\text{C} / 50\% \, \text{r} \, \text{h})$.

TAPE JOINTS

Thermal welding and hot air ensure the elasticity of all CEMLINE TAPE connections.

Welding temperatures:

tape thickness 1 mm: approx. 270 °C tape thickness 2 mm: approx. 360 °C

Overlap at butt joints: straight joints ≥ 3 cm, corner joints ≥ 2 cm. Before welding, roughen the contact area with sand paper.

CHEMICAL RESISTANCE

<u>Good resistance to:</u> water based bituminous coatings, water, cement, lime water and sea water, municipal sewage, UV-radiation, hydrolysis, microorganisms.

<u>Limited resistance to:</u> concentrated alkalis/acids, organic solvents (hydrocarbons, esters, ketone)

<u>pH limitations:</u> Depending on the average temperature, the pH-range should be limited as follows: pH = 2 to 10 ($< 30 \,^{\circ}$ C); pH = 5 to 10 ($< 40 \,^{\circ}$ C); pH = 6 to 8 ($< 60 \,^{\circ}$ C).

HEALTH AND SAFETY

Please refer to Safety Data Sheets of CEMLINE TAPE and adhesive on www.vandex.com.

TECHNICAL DATA					
Tape thickness		1,0	2,0		
Material		TPE	TPE		
Surface		smooth	smooth		
Colour	[RAL]	approx. 7045 (light grey)	approx. 7045 (light grey)		
Tearing strength		>6	>6		
Elongation at rupture		>400	>400		
Cold-weather performance		up to –30 °C no cracks	ut to –30 °C no cracks		
Maximum permissible expansion					
under continuous load	[% *]	10	20		
	of the unbonded flex zone				
Pre-requisite: min. adhesive cover on both sides = 100 mm					

All data is averaged from several tests under laboratory conditions. In practice, climatic variations such as temperature, humidity, and porosity of substrate may affect these values.

The information contained herein is based on our long-term experience and the best of our knowledge. We can, however, make no guarantee since for a successful outcome, all circumstances in an individual case must be taken into consideration. Indications of quantities required are only averages which in certain cases might be greater.



HEAD OFFICE AND INTERNATIONAL SALES: Vandex International Ltd

P.O. Box · CH-4501 Solothurn/Switzerland +41 32 626 36 36 · info@vandex.com · www.vandex.com



PRODUCTION: Vandex Isoliermittel-Gesellschaft m.b.H. P.O. Box · D-21487 Schwarzenbek/Germany



